

Mortar Mixing Instructions

- Empty contents of bag into a traditional concrete mixer
- Start mixer then add approx 4 to 5 litres of clean water per 25kg bag
- Mix continuously for 3 to 4 minutes until the required workability and consistency is achieved
- Colours are developed by the mixing action. Under or over mixing will result in incorrect colour
- Over mixing will be detrimental to strength and durability of the mortar
- Do not add any additional materials. All components required are within the mix
- Do not re-temper or add further water after initial set

Additional information

- The mortar is ready for pointing once laid when stiffened to the point that a thumb-print is barely visible
- Mortar should be pointed at a consistent stiffness. Failure to do so may result in colour variation
- Normal site curing practices should be followed including protecting the brickwork after construction



EuroMix

Helpline: 0845 850 9090

Visit us at: www.euromix.com **E-mail:** info@cpieuromix.com